

GRAPHENE QUANTUM DOTS AS PROMISING NANOSTRUCTURES FOR STUDYING REDOX PROCESSES IN NEUTROPHILS

Tatsiana Kulahava¹, Lena Golubewa^{1,2*}, Danielis Rutkauskas², Kiryl Barysau^{1,3}, Alena Kavalenka³, Renata Karpicz², Polina Kuzhir^{1,4}

¹ Institute for Nuclear Physics, Belarusian State University, Minsk, Belarus

² State research institute Center for Physical Sciences and Technology, Vilnius, Lithuania

³ Faculty of Physics, Belarusian State University, Minsk, Belarus

⁴ Institute of Photonics, University of Eastern Finland, Joensuu, Finland

* lena.golubewa@ftmc.lt

Graphene quantum dots (GQDs) belong to the group of promising nanomaterials for the development of bio-sensing systems. GQDs consist of several sp²-hybridized graphene sheets, with a lateral size from several to 10 nm. The GQDs edge can be functionalized with hydroxyl, carbonyl, carboxyl groups. Functionalized GQDs are water-soluble and more stable in physiological media than graphene oxide. GQDs can also act as a donor/acceptor of electrons [1], thus being sensitive to reduction/oxidation processes in living systems, e.g., neutrophils.

The aim of this work was to investigate the mechanisms of interaction of GQDs with human neutrophils and reveal the potential for the detection of reactive oxygen and chlorine species (ROS/RCS) during cell activation. Neutrophils were isolated from the whole blood of healthy donors. GQDs were added to the cells at a concentration of 50 µg/mL, the incubation time was 30-90 min. Intracellular GQDs distribution, F-actin reorganization, myeloperoxidase (MPO) redistribution and release were performed via fluorescence microscopy.

Incubation of neutrophils with GQDs for 30 minutes led to their accumulation in cells and cell activation, although no cytotoxic effect was revealed. A more pronounced activation of neutrophils exposed to GQDs for 90 minutes was observed. This was manifested in a greater spreading of cells than in control, in the modification of actin cytoskeleton, secretion of MPO to the outer space and the formation of neutrophil extracellular trap-like structures. The intensity of GQDs fluorescence in neutrophils after 30 min of cell adhesion was three times higher than after 90 min of adhesion, indicating the destruction and/or disruption of the GQDs structure after penetration into neutrophils (Fig. 1). Hypochlorite ions, produced via neutrophils activation and MPO release led to a decrease in the GQD fluorescence via their structure changes allowing to estimate the intensity of reduction/oxidation processes (RCS increase).




Fig. 1. Interaction of GQDs with neutrophils during cell adhesion: a – fluorescence images of neutrophils accumulated GQDs over 30 min, b – fluorescence images of cells accumulated GQDs over 90 min, c – fluorescence spectra of cells accumulated GQDs and in control cells. $\lambda_{\text{ex}} = 470$ nm, $\lambda_{\text{em}} = 525$ nm.

References

1. Fanping Shi, et al. J. Mater. Chem. B. 4 (2016) 3278.